

PLASTIKA KRITIS SA

PRODUCT DATA SHEET

PRODUCER	PLASTIKA KRITIS SA
PRODUCT	KRITIFLEX 6060

DESCRIPTION	Ethylene vinyl acetate (EVA) geomembrane
NOMINAL THICKNESS (mm)	0.5
THICKNESS TOLERANCE	Minimum : - 10 % Maximum : + 10 %

MECHANICAL PROPERTIES	TEST METHOD	TYPICAL VALUES
CARBON BLACK CONTENT (%)	OEE 8.2.4-02-01	2-3
CARBON BLACK DISPERSION (note)	NFT 51142	≤ 3
DENSITY OF MEMBRANE (g/cm³)	ASTM D792	0.950
MELT FLOW INDEX (g/10min.190°C)	ASTM D1238	0.40
TENSILE STRENGTH AT YIELD (N/mm²)	ASTM D638IV	
-MACHINE DIRECTION		4.5
-TRANSVERSAL DIRECTION		4.5
TENSILE STRENGTH AT BREAK (N/mm²)	ASTM D638IV	
-MACHINE DIRECTION		29.0
-TRANSVERSAL DIRECTION		29.0
ELONGATION AT YIELD (%)	ASTM D638IV	
-MACHINE DIRECTION	Gauge Length	24.0
-TRANSVERSAL DIRECTION	33mm	24.0
ELONGATION AT BREAK(%)	ASTM D638IV	
-MACHINE DIRECTION	Gauge Length	850
-TRANSVERSAL DIRECTION	50mm	850
PUNCTURE RESISTANCE (N)	ASTM D4833	140
TEAR RESISTANCE (N)	ASTM D1004C	
-MACHINE DIRECTION		40
-TRANSVERSAL DIRECTION		40
OXIDATIVE INDUCTION TIME (min)	ASTM D3895	>100



The typical values refer to results obtained in our laboratory during Quality Control of various production batches

P.O Box 1093, 711 10 Iraklion Crete Greece
 Tel:+30 2810 308500 Fax:+30 2810 381328 Tlx:262147 MC GR
 Email: r&d@plastikakritis.com

LIMIT OF LIABILITY

PLASTIKA KRITIS SA warrants that its products conform to PLASTIKA KRITIS' specifications for these products. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, STATUTORY OR OTHERWISE, INCLUDING BUT NOT LIMITED TO MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. Buyer assumes all risks and responsibility for results or inquiry in use or handling of the products or their suitability for any particular end use. The amount of any claim against PLASTIKA KRITIS and PLASTIKA KRITIS' liability shall in no event exceed the purchase price of the product. In no event shall PLASTIKA KRITIS SA be liable to Buyer for loss of profits or special, indirect or consequential damage.